

TCP™100-50-01A Thermally Conductive plastic

TCP™100-50-01A is a Thermally Conductive Engineering Plastic developed for the housing design which requires high thermally conductivity and reduces the weight more than 30% comparing with the same aluminium devices.



Application

TCP™100-50-01A can be used in applications such as Heat Sinking Housing at LED-lit BLU in LCD/LED TV and LED-lit lamps such as MR16. Also it can replace the normal Aluminum heat sink.

Features

- » Good thermal conductivity: 5.0W/mK
- » Excellent thermal conductivity compared to normal
 - engineering plastics
- » Lighter than normal Aluminum housing 30% in weight
- » Excellent mould ability in injection moulding
- » Much higher production yield than normal

Typical Properties of TCP [™] 100-50-01A				
Items	Test method	Unit	Typical data	
Physical Properties				
Material	****	****	Nylon	
Color	Visual	****	Black	
Melt index	ASTM D1238	g/10min	4	
Specific Gravity	ASTM D792	g/cm ³	1.45	
Shrinkage	ASTM D955	%	0.1	
Mechanical Properties				
Tensile Strength	ASTM D638	MPa	55	
Flexural Strength	ASTM D790	MPa	80	
Flexural Modulus	ASTM D638	MPa	15800	
Impact Strength, notched	ASTM D256	kJ/m ²	2.5~3.5	
Electrical Properties				
Dielectric Constant, 1MHz	ASTM D150	***	4.5	
Volume Resistivity	ASTM D257	Ohm-meter	10000	
Thermal Properties			•	
Heat Deflection Temperature	ASTM D648	$^{\circ}\! \mathbb{C}$	150	
Vicat Temperature	ASTM D648	$^{\circ}\!\mathbb{C}$	15.0	
Thermal Conductivity Throngh Plane	ASTM E1461	W/m-K	5.0	
Flame Retardancy	Min. thick. 1.0mm	Class	V-0	

^{*}These are typical values and should not be used for establishing product specification. The properties may vary upon the machine process under use. For more information please contact Ziitek Tech directly.

Gap Fillers | Pouring sealant | Silicon tape | Thermally Conductive paste | Flake graphite | Thermally Conductive Insulators | Ceramic heat | Thermally Conductive plastic | Thermally Conductive Adhesive Tapes

Canada: Tel:+001-604-2998559 E-mail: sales@thermazig.com Taiwan:
Tel: +886-2-22771007
Fax: +886-2-22771075
E-mail: frances@ziitek.com.tw

Dongguan:
Tel: +86-769-38801208
Fax: +86-769-83791290
E-mail: angus@ziitek.com

Kunshan:
Tel: +86-512-57816297
Fax: +86-512-57816327
E-mail: kelvin@ziitek.com

Hangzhou: Tel: +86-0571-63850366 Fax: +86-0571-63850322 E-mail: alex@ziitek.com



Injection Parameters of Recommends

TCP [™] 100-50-01A Injection parameters		Value Range
	One sect / °C	240-260℃
Barrel Zone Temperature	Two sect / °ℂ	250-270℃
	Three sect / $^{\circ}\!\mathbb{C}$	260-280℃
Mouth Temperature / °C		265-280℃
Melt Temperature / °C		250-280℃
Bake Temperature / °C		100-120℃ 4H
Mould Temperature / °ℂ		80-100℃
Injection Pressure / Bar		3-9Мра
Injection Speed / mm/s		Medium speed

Remarks:

Data from the laboratory of the Division I 1 above are for reference only, not as a product standard reference.

2 The typical processing conditions according to different models, different mold and product requirements to make the appropriate adjustments.

Handling & Safety

TCP™100 should be used in accordance with good industrial practice. For more detailed information please contact Ziitek technical service group.

Supply Appearance And Standard Packing

TCP™100 is supplied in regular pellet form packaged in polyethylene bags.

Net weight is 25kg per bag. For more information please contact us.



Gap Fillers | Pouring sealant | Silicon tape | Thermally Conductive paste | Flake graphite | Thermally **Conductive Insulators** | Ceramic heat sinks **Thermally Conductive plastic** Thermally Conductive Adhesive **Tapes**

Canada:

Tel:+001-604-2998559 E-mail: sales@thermazig.com <u>Taiwan:</u>

Tel: +886-2-22771007 Fax: +886-2-22771075 E-mail: frances@ziitek.com.tw Dongguan:

Tel: +86-769-38801208 Fax: +86-769-83791290 E-mail: angus@ziitek.com Kunshan:

Tel: +86-512-57816297 Fax: +86-512-57816327 E-mail: kelvin@ziitek.com Hangzhou:

Tel: +86-0571-63850366 Fax: +86-0571-63850322 E-mail: alex@ziitek.com

The information and statements herein are believed to be reliable but are not to be construed as a warranty or representation for which we assume legal responsibility. Users should undertake sufficient verification and testing to determine the suitability for their own particular purpose of any information or products referred to herein.